

TILE ADHESIVE EX-G-33 (EX 33 Grey)

Tile Adhesive Ex-G-33 is a high polymer modified, Portland cement-based tile adhesive applicable for fixing vitrified/ fully vitrified tiles, glass mosaic tiles, all stones, dense and large dimension tiles & slabs. It is mainly suitable for tiles with an apparent porosity less than or equal to 3%. It is more demanding for wet areas, submerged areas, etc. Tile Adhesive EX-G-33 consists of cement, graded sand, and specialized polymers which combine to give high bond strength, water retention, superior workability, and unique properties.

PRODUCT DESCRIPTION

PRODUCT: Grey cementitious adhesive for fixing tiles for thin bed applications develops high- efficiency, high strength and high-quality.



COMPOSITION	Graded sand, cement, selected fillers, polymers
COLOUR	Gray dry powder
TESTS	Tested according to IS 15477:2019
FEATURES	<ul style="list-style-type: none">• No shrinkage• Increase productivity• No curing required• Highly water resistant• No need for hacking• Excellent adhesion to base plaster/ concrete surface
USES	<ul style="list-style-type: none">• Suitable for interior walls & floors, exterior only Floor applications• Can be used for new/ old walls and tile-on-tile application• Consistent work quality• High durability• Negligible waste• Save time

TECHINCAL DATA SHEET
TECHNICAL ANALYSIS (TYPE II: CONFORMS TO IS 15477:2019)

PARAMETERS	SPECIFICATIONS
Spread ability	Spread easily with good notch ability
Open time	≥ 20 minutes
Adjustability	≥ 20 minutes
Slip resistance	< 0.5 mm
Pot life	> 120 minutes
Density	1.5 -1.9 g/ml
Tensile Adhesion Strength (Dry Condition, After 28 Days)	Minimum 1.0 N/mm ²
Tensile Adhesion Strength (Wet Condition, After 28 Days)	Minimum 1.0 N/mm ²
Shear Adhesion Strength (Dry Condition, After 28 Days)	Minimum 1.25 N/mm ²
Shear Adhesion Strength (Heat Aging Condition, After 28 Days)	Minimum 1.0 N/mm ²
Shear Adhesion Strength (Wet Condition, After 28 Days)	Minimum 1.0 N/mm ²

GUIDANCE FOR USE

SUBSTRATE	<ul style="list-style-type: none"> • Cement based backgrounds • Cement plaster • Cement concrete • Cement screed • Tiles and stone tiles on exterior substrate
SUBSTRATE PREPARATION	<ul style="list-style-type: none"> • Clean loose particles, dirt, grease and traces of foreign materials from the surface, if necessary, by using wire brush/sandpaper or by chipping. • For loose plaster areas or floors/wall which are not even, then remove the defective material and re-plaster the area with Ready-Mix Plaster to make them even.
MIXING	<ul style="list-style-type: none"> • Take approx. 200-300 ml of clean water for 1 Kg of Tile Adhesive EX-G-33 in a clean bucket. It is very important that add material into water and not vice versa. • Stir continuously for 3-5 minutes by using mechanical stirrer or by hand to obtain a homogeneous lump-free paste. • Allow the resultant paste to stand for about 10 minutes for the additives to dissolve. • Re-mix again for about 2 minutes. The mixture is now ready to apply.

TECHINCAL DATA SHEET

APPLICATION	<ul style="list-style-type: none"> Dampen the surface to be plastered with clean water. Allow excess water to drain off. The tiles should be immersed in water for about two hours before fixing. Apply the material with the help of putty patra/ blade, use 6mm notched trowel for application. Application should be angled between 35 to 45 degrees, using the right amount of pressure. Check for holes and gaps in the adhesive, spread it evenly. Fix the tile in the place and tap gently with wooden hammer. Using a notched trowel remove excess mixture from the tile and clean it by using a damp cloth or sponge.
COVERAGE	<ul style="list-style-type: none"> 50 – 60 sq. ft./ Bag (20 Kg) at 3mm thickness on plain surface (Or depending on substrate conditions).
USAGE	<ul style="list-style-type: none"> Do not add more water than recommended.
PRECAUTIONS	<ul style="list-style-type: none"> Maximum adhesive thickness 3-12mm. Do not directly used on gypsum plaster surface, paint, wood and metal. Before tile-on-tile application, ensure that the original tiling surface has enough roughness to provide the required high strength bonding.
PACK SIZE	<ul style="list-style-type: none"> 20 Kg
SHELF LIFE	<ul style="list-style-type: none"> 12 months

STORAGE INSTRUCTIONS

- Store in cool, dry, and well-ventilated place away from heat source or direct sunlight.
- Keep away from water and damp area.
- Avoid using partially used material; open bags with partially used material should be kept in a bag with its mouth tied tightly with string to prevent lump formation.
- As temperature, humidity, water addition and other parameters vary from site to site; the above information should be treated as general guidelines.

HEALTH & SAFETY INFORMATION

- It contains only eco-friendly fillers and additives. However, being cement-based, it is alkaline and hence it is advisable to avoid direct eye and skin contact with this. In case of eye contact, kindly wash with clean water at least for 15 minutes, seek medical help, and keep it out of children's reach.

Disclaimer: Technical information is based on knowledge and experience of accurate results. These results refer to the long-term application of the product in practice. Recommendations and suggestions are listed for guidance only. Since site conditions during the applications are beyond the manufacturer's control, hence it is also the responsibility of the end-user to ensure that the content in their possession is the latest case.